



## Slabs unfaced – Density 24 kg/m<sup>3</sup>

ULTIMATE mineral wool provides a unique high-performance profile: It combines safety, comfort and ease of handling.



### FIRE RESISTANCE

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire.



### THERMAL INSULATION

Excellent thermal insulation combined with unique efficiency.



### SOUND ABSORPTION

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties.



### LIGHTWEIGHT

Increase insulation – reduce weight. ULTIMATE combines high fire & thermal performance with very low weight.



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES						STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	DIN EN 12667
	$\lambda_{NR}$	[W/(m•K)]	0.034	0.040	0.049	0.062	0.080	0.124	
Thermal behaviour	T	[°C]	≤ 650 by pure thermal stress (U SeaProtect Slab 40 - 100) ≤ 600 by pure thermal stress (U SeaProtect Slab 24 - 40) U SeaProtect Slab: The thickness of the insulating layer has to be correctly dimensioned so that the faced side is exposed to a maximum of 100°C. From 150°C on the binder starts to volatilise.						AGI Q 132

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	VALUES	STANDARD
Air flow resistivity	$\sigma$	[KPa• s/m²]	Density 24 kg/m³	15	DIN EN 29053

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: ≥ 1000°C. Non combustible according to IMO-Resolution MSC.61(67)-(FTP-Code), IMO MSC/Circ. 1120. Homologated for shipbuilding according to EC Type Examination Certificate Nr.: 114.477 U SeaProtect Slab 90: certified construction for A 60 (floating floor) 100.185; top-layer only according to static calculation	EN 13501-1
Chemical behaviour	-	-	[ERROR READING XHTML FRAGMENT]	AGI Q132 EN 13468 ASTM C795
Application field	-	-	Thermal insulation, acoustic insulation and fire protection constructions in shipbuilding.	EN 14303
Material	-	-	Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle e.V., unrisky regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to guideline EU 97/69 Nota Q.	CINI 2.1.05
Water vapour diffusion resistance factor	$\mu$	-	~ 1.0	-
Thermal coefficient of expansion	$\alpha$	1/K	No change in dimensions within the application field.	-
Instructions for transformation	-	-	[ERROR READING XHTML FRAGMENT]	-
Instructions for use	-	-	suitable for thermal and acoustic insulation, fire protection A-30 Deck; A-15 Bulkhead	-
Quality management	-	-	ISOVER is certified according to DIN EN ISO 9001 and DIN EN ISO 14001.	EN ISO 9001 EN ISO 14001



## DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\*

THICKNESS D [MM]	WIDTH B [MM]	LENGTH [MM]
100	600	1200
30	600	1200
40	600	1200
50	600	1200
60	600	1200
70	600	1200
80	600	1200

\* On some products, minimum order quantities are requested.

\*\* Further dimensions on request.



### [www.isover-technical-insulation.com](http://www.isover-technical-insulation.com)

*The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.*

**SAINT-GOBAIN ISOVER** · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France