



## U SeaProtect Roll 24 G120

### Rolls glass cloth faced G120 - density 24 kg/m<sup>3</sup>

ULTIMATE mineral wool provides a unique high-performance profile: it combines safety, comfort and ease of handling.



#### FIRE RESISTANCE

ULTIMATE provides effective fire resistance, but also very good performance in reaction to



#### THERMAL INSULATION

Excellent thermal insulation combined with unique efficiency



#### SOUND ABSORPTION

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties



#### LIGHTWEIGHT

Increase insulation - reduce weight  
ULTIMATE combines high fire & thermal performance with very low weight



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES						STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	EN 12667
	$\lambda_{NR}$	[W/(m•K)]	0.034	0.040	0.049	0.062	0.080	0.124	
Thermal behaviour	T	[°C]	Exposure to temperature until 400 °C (depends on density) is possible From 150 °C on the binder starts to volatilise						AGI Q 132

CHARACTERISTIC	SYMBOL	UNIT	THICKNESS	VALUES	STANDARD
Sound absorption value	$\alpha_w$	-	50 mm	1.00	-
			100 mm		

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	VALUES	STANDARD
Air flow resistivity	$\sigma$	[KPa•s/m <sup>2</sup> ]	Density 24 kg/m <sup>3</sup>	15	DIN EN 29053

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Specific thermal capacity	c	kJ/(kg•K)	1.03	ISO 10456
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: © 1000 °C. Non combustible according to IMO-Resolution MSC.61(67)-(FTP-Code), IMO MSC/Circ. 1120. Homologated for shipbuilding according to EC Type Examination Certificate Nr. 114.529	DIN 4102-17 IMO-Resolution MSC.307(88)- (FTP-Code 2010)
Chemical behaviour	-	-	Sulphide free.	-
Application field	-	-	Thermal insulation, acoustic insulation and fire protection constructions in shipbuilding.	-
Material	-	-	Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle e.V., unriskey regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to guideline EU 97/69 Nota Q.	-
Facing	-	-	U SeaProtect Rolls 20 G120 to 36 G120 are faced on one side with a glass fiber tissue with a gram weight of - 120 g/m <sup>2</sup> .	-
Water vapour diffusion resistance factor	$\mu$	-	- 1	ISO 10456
Quality management	-	-	ISOVER is certified according to DIN EN ISO 9001 and DIN EN ISO 14001.	EN ISO 9001 EN ISO 14001
Type approval certificates			EC-Type Examination MED-B (Non Combustibility): 114478-06 exp. 08/03/2028 EC-Type Examination MED-B (Low Flame Spread): 118168-04 exp. 22/10/2028 QAS MED-D Certificate: SEE0736Q0000108 exp. 19/05/2027	

### DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\*

THICKNESS D [MM]	WIDTH B [MM]
100	1200
120	1200
30	1200
40	1200
50	1200
60	1200
80	1200

\* All dimensions require minimum order quantities / other dimensions on request.



## U SeaProtect Roll 24 G120



### [www.isover-technical-insulation.com](http://www.isover-technical-insulation.com)

*The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.*

**SAINT-GOBAIN ISOVER** · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France

AUG-2024

