



U SeaProtect Slab 50 B-AI

Slabs with an alu-coated glass fabric, alu side outside-Density 50 kg/m³

ULTIMATE mineral wool provides a unique high-performance profile: It combines safety, comfort and ease of handling



FIRE RESISTANCE

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire.



THERMAL INSULATION

Excellent thermal insulation combined with unique efficiency.



SOUND ABSORPTION

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties.



LIGHTWEIGHT

Increase insulation - reduce weight. ULTIMATE combines high fire & thermal performance with very low weight.

U SeaProtect Slab 50 B-AI



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES							STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	400	EN 14706
	$\lambda_{N,R}$	[W/(m·K)]	0.031	0.036	0,042	0,050	0,059	0,080	0,109	
Thermal behaviour	T	[°C]	≤ 650 by pure thermal stress (U SeaProtect Slab 40 - 90) The thickness of the insulating layer has to be correctly dimensioned so that the faced side is exposed to a maximum of 100 °C. From 150 °C on the binder starts to volatilise.							EN 14706

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	VALUES	STANDARD
Air flow resistivity	σ	[KPa· s/m ²]	Density 50 kg/m ³	[40-60]	DIN EN 29053

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Specific thermal capacity	c	kJ/(kg·K)	1.00	ISO 10456
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: 1000 °C. Non-combustible according to IMO-Resolution MSC.61(67)-(FTP-Code), IMO MSC/Circ. 1120. Surface materials with low flame-spread characteristics.	RESOLUTION MSC.307(88) (2010 FTP CODE)
Application field	-	-	Thermal, acoustic insulation and fire protection constructions in ship-building. Approved for A-Class steel constructions.	-
Material	-	-	Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle. V., unriskey regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to guideline EU97/69 Nota Q.	-
Facing	-	-	One-sided faced with Alu-coated glass fabric, with aluminium side outside Gramweighth of the facing: approx. 260 g/m ² .	-
Water vapour diffusion resistance factor	μ	-	- 1.0	-
Thermal coefficient of expansion	α	1/K	No change in dimensions within the application field.	-
Quality management	-	-	Certified according to DIN EN ISO 9001 and DIN EN ISO 14001.	EN ISO 9001 EN ISO 14001
Type approval certificates			EC-Type Examination MED-B (Non Combustibility): 114477-05 exp. 08/03/2028 EC-Type Examination MED-B (Low Flame Spread): 118428-01 exp. 07/08/2027 QAS MED-D Certificate: SEE0736Q0000108 exp. 19/05/2027	

DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION*

THICKNESS D [MM]	WIDTH B [MM]	LENGTH [MM]
25	625	1200
30	625	1200
50	625	1200
60	625	1200

*On some products, minimum order quantities are requested.

** Further dimensions on request.



www.isover-technical-insulation.com

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.

SAINT-GOBAIN ISOVER · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France

AUG-2024

