



## U TECH Pipe Section MT 4.0

### The **ULTIMATE** solution for industry pipe insulation

U TECH Pipe Section MT 4.0 is the efficient and light alternative for the insulation of industry process pipelines for standard pipe diameters from 15 mm to 356 mm (1/2" to 14"). The **ULTIMATE** mineral wool preformed concentric-rolled pipe section is equipped with a pre-slit to facilitate the opening and fitting over the pipes.

U TECH Pipe Section MT 4.0 are light and easy to handle. With a length of 1.2 m, installation time on straight pipes and thermal bridges through joints can be reduced by 20 %.

U TECH Pipe Section MT 4.0 can be used for service temperatures of up to 660 °C.



#### **HIGH SERVICE TEMPERATURES**

Especially designed for high service temperatures up to 660 °C



#### **COST EFFECTIVE SOLUTION**

Thermal performance combined with lightweight provides installation time saving and less heat loss costs



#### **THERMAL INSULATION**

Thermal performance for service temperatures up to 660° C with up to 35 % better efficiency than standard solutions



#### **FAST INSTALLATION**

By cut-to-fit dimension, it reduces weight per piece and can be handled by one person only  
No need of spacers or similar



#### **NUCLEAR PLANT QUALITY**

For use in nuclear applications



#### **FIRE REACTION**

Non-combustible, Euroclass A1 for effective fire protection on industry sites

# U TECH Pipe Section MT 4.0



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES						STANDARD
Thermal conductivity	T	[°C]	40	50	100	150	200	300	ASTM C335 ISO 8497 EN ISO 13787
	λ	[W/(m·K)]	0.035	0.037	0.043	0.052	0.062	0.092	
Thermal behaviour	T	[°C]	Maximum service temperature 660 (under 500 Pa) Maximum service temperature 700						EN 14707 C447/C411

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES						STANDARD
Specific thermal capacity	c	kJ/(kg·K)	1.03						ISO 10456
Reaction to fire	-	-	Non combustible; Euroclass A <sub>1L</sub>						EN 13501-1
Water behaviour	WS	kg/m <sup>2</sup>	No short term water absorption by partial immersion (WS1 ≤ 1 kg/m <sup>2</sup> )						EN 13472
Chemical behaviour	-	-	AS-quality (Leachable Chloride ≤10ppm) Leachable chloride content less than 10 ppm (CL10) Do not contribute to corrosion of stainless steel						AGI Q132 EN 13468 ASTM C795/871
Application field	-	-	Product for use in technical applications, such as big diameter pipes, exhaust ducts and stacks, with need for: thermal and/or acoustic insulation with high performances especially at high temperatures. Especially designed and certified for use in nuclear applications.						EN 14303 PMUC
Linear Shrinkage	-	%	<2% (at 700°C)						ASTM C356
Material	-	-	ULTIMATE mineral wool, preformed concentric in shape of pipe section. With quality marks EUCEB and RAL by the Gütegemeinschaft Mineralwolle e. V., unriskey regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to regulation EC No 1272/2008 Note Q						CINI 2.2.03
Miscellaneous	-	-	Insulating material identification number: 10.04.03.99.99 Designation code : MW-EN14303-T8-ST(+)-660-WS1-CL10 (outside pipe ø ≤ 150 mm) Designation code : MW-EN14303-T9-ST(+)-660-WS1-CL10 (outside pipe ø > 150 mm)						AGI Q 132 EN14303
Quality management	-	-	CE-marked according to EN 14303 Quality control according to VDI 2055 ISOVER is certified according to EN ISO 9001 and EN ISO 14001						EN 14303 EN ISO 9001 EN ISO 14001

# U TECH Pipe Section MT 4.0



## DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\*

THICK- NESS D [MM]	DIAMETER Ø [MM]																						
	15	18	22	28	35	42	48	54	57	60	64	70	76	89	102	108	114	133	140	159	168	219	273
20	57.6	50.4	43.2	36.0	30.0	24.0	19.2	28.8	28.8	27.6	24.0			16.8									
30	30.0	28.8	24.0	19.2	19.2	14.4	24.0	19.2	19.2	19.2	18.0	14.4	14.4	10.8	9.6	9.6	7.2	6.0	6.0	4.8	4.8	1.2	1.2
40		28.8	14.4	19.2	10.8	10.8	9.6	10.8	10.8	10.8	10.8	10.8	10.8	9.6	7.2	7.2	6.0	4.8	4.8	4.8	3.6	1.2	1.2
50			18.0	14.4	10.8	10.8	10.8	10.8	10.8	9.6	9.6	9.6	4.8	4.8	6.0	6.0	4.8	4.8	3.6	3.6	1.2	1.2	1.2
60			10.8	10.8	10.8	9.6	9.6	4.8	4.8	4.8	4.8	4.8	6.0	4.8	4.8	4.8	4.8	3.6	1.2	1.2	1.2	1.2	1.2
70										4.8	4.8	4.8	4.8	4.8	3.6	3.6	3.6	1.2	1.2	1.2	1.2	1.2	1.2
80						6.0	4.8					4.8	4.8	3.6	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2
90														1.2									
100													1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2
120																				1.2	1.2	1.2	

\* The information refers to linear meters / pack.  
All dimensions require minimum order quantities / other dimensions on request.



[www.isover-technical-insulation.com](http://www.isover-technical-insulation.com)

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.

SAINT-GOBAIN ISOVER · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France

OCT-2025

