



U SeaProtect Roll 36 V2

Rolls glass veil faced – Density 36 kg/m³

ULTIMATE mineral wool provides a unique high-performance profile: It combines safety, comfort and ease of handling.



FIRE RESISTANCE

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire



THERMAL INSULATION

Excellent thermal insulation combined with unique efficiency



SOUND ABSORPTION

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties



LIGHTWEIGHT

Increase insulation - reduce weight
ULTIMATE combines high fire & thermal performance with very low weight



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES							STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	400	EN 12667
	λ_{NR}	[W/(m·K)]	0.032	0.037	0.045	0.055	0.069	0.104	0.153	
Thermal behaviour	T	[°C]	Exposure to temperature up to 400 °C (depends on density) is possible on the unfaced side, but the thickness of the insulating layer has to be correctly dimensioned so that the faced side is exposed to a maximum of 100 °C. From 150 °C on the binder starts to volatilise.							AGI Q 132

CHARACTERISTIC	SYMBOL	UNIT	THICKNESS	VALUES	STANDARD
Sound absorption value	α_w	-	70 mm	1.00	-

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	VALUES	STANDARD
Air flow resistivity	σ	[KPa/m ²]	Density 36 kg/m ³	30	DIN EN 29053

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Specific thermal capacity	c	kJ/(kg·K)	1.03	-
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: ≥ 1000 °C Non combustible according to IMO-Resolution Homologated for shipbuilding according to EC Type Examination Certificates Nr.: MED-B+D Certificate = visit our website	DIN 4102 IMO
Chemical behaviour	-	-	Sulphide free	-
Application field	-	-	Thermal insulation, acoustic insulation and fire protection constructions in shipbuilding	-
Material	-	-	Mineral wool with quality mark RAL by the Gütegemeinschaft Mineralwolle e.V., unriskey regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to Regulation (EC) N°1272/2008	-
Facing	-	-	U SeaProtect Rolls V2 are faced with black glass tissue	-
Water vapour diffusion resistance factor	μ	-	~ 1.0	EN 12086
Quality management	-	-	ISOVER is certified according to DIN EN ISO 9001 and DIN EN ISO 14001	EN ISO 9001 EN ISO 14001
Type approval certificates	-	-	EC-Type Examination MED-B (Non Combustibility): 114478-06 exp. 08/03/2028 EC-Type Examination MED-B (Low Flame Spread): 118156-04 exp. 02/01/2029 QAS MED-D Certificate: SEE0736Q0000108 exp. 19/05/2027	

DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION*

THICKNESS D [MM]	WIDTH B [MM]
70	1200

* All dimensions require minimum order quantities / other dimensions on request.



www.isover-technical-insulation.com

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.

SAINT-GOBAIN ISOVER · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France

