



## TECH Tank Roof Slab 50 kPa

ISOVER Tank Roof Slab  
50 kPa

**High performance compressive strength stone wool slabs for the thermal, acoustic and fire protection insulation of industrial applications such as tank roofs.**

TECH Tank Roof Slab 50 kPa is a rigid stone wool slab for industry applications requiring high mechanical resistance such as flat tank roofs or other equipment with a maximum service temperature of up to 700°C. It combines premium thermal and acoustic efficiency with high compressive strength performance.

TECH Tank Roof Slab 50 kPa is available with AS-Quality (Cl<sup>-</sup> ≤10ppm) when in contact with austenitic steel structures. TECH Tank Roof Slab 50 kPa was specifically designed to fulfill the highly demanding requirements of Swedish standard SSG7591 and CINI (2.2.01) making it strong enough to withstand normal walking loads during installation and maintenance.



#### MECHANICAL RESISTANCE

Robust industry slab for optimal use in applications requiring high mechanical strength, e.g. by foot traffic



#### ENERGY EFFICIENCY

Thermal insulation performance at medium to higher service temperatures up to 700 °C



#### HIGH SERVICE TEMPERATURES

Especially designed for high service temperatures up to 700°C



#### FIRE REACTION

Non-combustible, Euroclass A1 for effective fire protection on industry sites

# TECH Tank Roof Slab 50 kPa



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES									STANDARD
Thermal conductivity	T	[°C]	50	100	150	200	300	400	500	600	700	EN 12667 EN ISO 13787
	$\lambda$	[W/(m·K)]	0,043	0,048	0,055	0,063	0,083	0,110	0,143	0,182	0,227	
Thermal behaviour	T	[°C]	Maximum service temperature 700									EN 14706
Air flow resistivity	-	kPa.s.m <sup>2</sup>	> 50									EN ISO 9053-1

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES									STANDARD
Specific thermal capacity	c	kJ/(kg·K)	0.80									-
Reaction to fire	-	-	Non-combustible; Euroclass A1									EN 13501-1
Mechanical Properties	CS	kPa	Compressive strength at 10 % deformation CS(10)50									EN 826
Water behaviour	WS	kg/m <sup>2</sup>	No short term water absorption by partial immersion (WS1 ≤ 1 kg/m <sup>2</sup> )									EN ISO 29767
Chemical behaviour	-	-	Leachable chloride content less than 10 ppm (CL10)D									EN 13468
Application field	-	-	Product for use in technical applications, such as tanks and vessels, exhaust ducts and stacks or other equipment with need for good thermal and/or acoustic insulation at high process temperatures. The slab fulfil the requirements of SSG 7591 for storage tank roof insulation (compressive strength resistance 50kPa).									-
Material	-	-	Stone mineral wool rigid board with quality marks EUCEB, unrisky regarding health according to regulation EC No 1272/2008 Note Q.									CINI 2.2.01
Miscellaneous	-	-	Designation code: MW - EN 14303 - T5 - ST(+)700 - CS(10)50 - WS1 - CL10									-
Quality management	-	-	CE-marked according to EN 14303 Isover is certified according to EN ISO 9001 and EN ISO 14001									EN 14303 EN ISO 9001 EN ISO 14001
Delivery form	-	-	Please contact your local ISOVER dealer All dimensions require minimum order quantities Standard width: 500mm Standard thickness range: 60mm until 140mm Other dimensions on request when fulfilling minimum volume									-

## DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\*

THICKNESS [MM]	DIMENSIONS [MM]	M <sup>2</sup> / PALLET	M <sup>2</sup> / PACKAGE	PACKAGE / PALLET	SLABS / PACKAGE
60	600 x 1200	30.24	2.16	14	3
80	600 x 1200	21.60	2.16	10	3
100	600 x 1200	17.28	1.44	12	2
120	600 x 1200	14.40	1.44	10	2
140	600 x 1200	11.52	1.44	8	2

Minimal volume need to be consulted with a producer.



### [www.isover-technical-insulation.com](http://www.isover-technical-insulation.com)

*The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.*

SAINT-GOBAIN ISOVER · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France

JUL-2025

