



## TECH Tank Roof Slab 60 kPa METAC FLP1 Duratec

### High performance compressive strength stone wool slabs for the thermal, acoustic and fire protection insulation of industrial applications such as tank roofs.

TECH Tank Roof Slab 60 kPa is a rigid stone wool slab for industry applications requiring high mechanical resistance such as flat tank roofs or other equipment with a maximum service temperature of up to 680°C. It combines premium thermal and acoustic efficiency with high compressive strength performance. TECH Tank Roof Slab 60 kPa is available with AS-Quality (Cl- ≤10ppm) when in contact with austenitic steel structures. TECH Tank Roof Slab 60 kPa was specifically designed to fulfill the highly demanding requirements of Swedish standard SSG 7591 and CINI (2.2.01) making it strong enough to withstand normal walking loads during installation and maintenance.

#### MECHANICAL RESISTANCE



Robust industry slab for optimal use in applications requiring high mechanical strength, e.g. by foot traffic

#### ENERGY EFFICIENCY



Premium thermal insulation performance at medium to higher service temperatures up to 680 °C

#### HIGH SERVICE TEMPERATURES



Especially designed for high service temperatures up to 680°C

#### FIRE REACTION



Non-combustible, Euroclass A1 for effective fire protection on industry sites

#### Thermal Efficiency Indicator

8. extra plus

7. extra

6. premium plus

5. premium

4. standard plus

3. standard

2. classic plus

1. classic

5.

# TECH Tank Roof Slab 60 kPa



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES									STANDARD
Thermal conductivity	T	[°C]	50	100	150	200	300	400	500	600	680	EN 12667 EN ISO 13787
	$\lambda$	[W/(m•K)]	0,042	0,047	0,053	0,062	0,084	0,112	0,147	0,189	0,228	
Thermal behaviour	T	[°C]	Maximum service temperature 700									EN 14706

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES									STANDARD
Specific thermal capacity	c	kJ/(kg•K)	1.03									-
Reaction to fire	-	-	Non combustible; Euroclass A1									EN 13501-1
Mechanical Properties	-	-	Compressive strenght at 10 % deformation CS(10)60									EN 826
Water behaviour	-	-	No short term water absorption by partial immersion (WS1)									EN ISO 29767
Chemical behaviour	-	-	On request : AS-quality (Leachable Chloride ≤10ppm) On request : Leachable chloride content less than 10 ppm (CL10)									AGI Q 132 EN 13468
Application field	-	-	Product for use in technical applications, such as tanks and vessels, exhaust ducts and stacks or other equipment with need for good thermal and/or acoustic insulation at high process temperatures. The slab fulfil the requirements of SSG 7591 for storage tank roof insulation (compressive strength resistance 60kPa).									-
Material	-	-	Stone wool with quality marks EUCER and RAL by the Gütegemeinschaft Mineralwolle e. V., unrisky regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to regulation EC No 1272/2008 Note Q.									-
Miscellaneous	-	-	Designation code : MW-EN 14303-T4-ST(+)-680-WS1-CS(10)60									-
Quality management	-	-	CE-marked according to EN 14303 ISOVER is certified according to EN ISO 9001 and EN ISO 14001									EN 14303 EN ISO 9001 EN ISO 14001

## DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION\*

THICKNESS D [MM]	WIDTH B [MM]	LENGTH [MM]	M <sup>2</sup> /PACK	M <sup>2</sup> /PALLET	SLABS/PACK	PACKS/PALLET
100	600	1200	1.44	17.28	-	12
120	600	1200	1.44	14.40	-	10
140	600	1200	1.44	11.52	-	8
80	600	1200	2.16	21.60	-	10

\* All dimensions require minimum order quantities / other dimensions on request.



## www.isover-technical-insulation.com

The technical information corresponds to our present state of knowledge and experience at the date of printing (see imprint). But no legal guarantee can be given, unless it has been explicitly agreed. The state of experience and knowledge is developing continuously. Please see to it that you always use the latest edition of this information. The described product applications do not take special circumstances in consideration. Please verify whether our products are appropriate for the concrete application. For further information please contact our Isover sales offices. We deliver only according to our terms of trade and terms of delivery.

SAINT-GOBAIN ISOVER · Tour Saint-Gobain 12 place de l'Iris 92096 La Défense cedex - France

MAR-2024

